

Nudura

NUBASE PARGING MIX



PRODUCT INFORMATION SHEET

Product Code

3009DS 501

Product Description

Nudura's NUBASE Parging Mix is a fibre-reinforced, polymer-modified, dry mix, cementitious base coat specifically formulated for use on Expanded Polystyrene (EPS) foam. The Parging Mix is used in conjunction with the Nudura Fiber Mesh to provide a solid, durable finish over the exposed portion of the Nudura form at grade.

Basic Uses

The Nudura NUBASE Parging Mix is used to provide a solid, durable finish over the exposed portion of the Nudura form typically between the final grade of a building and the intended above grade finish material.

Application

The surface of the Nudura form must be rasped and cleaned prior to the parge coat application. Nudura's NUBASE Parging Mix is combined on site with clean, potable water and applied to the surface of the Nudura form. The NUBASE parge coat is applied in a two-coat process with the Nudura Fiber Mesh embedded in the base coat layer. For complete installation instructions please refer to Nudura's website at www.nudura.com.

Packaging

Nudura's NUBASE Parging Mix is packaged in a durable bag.

Bag Length: 20" (508 mm)

Bag Width: 5" (127 mm)

Bag Height: 14" (336 mm)

Bag Weight: 50 lbs (23kg)



Nudura

NUBASE PARGING MIX



Storage

Store the NUBASE Parging Mix bags off the ground in a clean, cool, dry location, out of direct sunlight. The parge coat bags must be protected from moisture and weather. Storing the parging mix bag in a warm or hot location will reduce the products shelf life.

The shelf life of an unopened NUBASE Parging Mix bag is 1 year from the date of manufacture when properly stored.

Estimating

To estimate the number of bags of Nudura NUBASE Parging Mix (PARG) required for a specific project, begin by determining the linear footage (linear meters) of the perimeter of the structure. Multiply the perimeter length by the width of the parge coat band required. Keep in mind the parge coat typically extends a few inches below grade or 1" (25 mm) over the top edge of the Waterproofing Membrane to the underside or 1" (25 mm) past the start of the exterior finish. Divide this calculated wall area by 41ft² (3.81 m²).

This estimate will calculate for a two-coat application, each coat being roughly 1/12" (2mm) – 1/8" (3mm) thick.

Imperial Calculation

$$\text{PARG} = (\text{LPPER} \times \text{Width of Parge}) \div 41\text{ft}^2$$

Metric Calculation

$$\text{PARG} = (\text{LMPER} \times \text{Width of Parge}) \div 3.81\text{m}^2$$

Watch our accessory videos on [Nudura's YouTube Channel](#)

This information is offered in good faith based on data available to us that we believe to be true and accurate. However, no warranty of merchantability, fitness for any particular purpose, or any other warranty is expressed or is to be implied regarding the accuracy or completeness of this information, the results to be obtained from the use of this information or the product, the safety of this product, or the hazards related to its use. The information provided herein, and the product, are furnished on the condition that the person receiving them shall make their own determination as to the suitability of the product for their particular purpose and on the condition that they assume the risk of their use. The manufacturer, supplier, nor any of its subsidiaries assumes any liability whatsoever for any damage or injury resulting from abnormal use or from any failure to adhere to recommended practices.

Nudura Inc., Oct 2020